



## DENSO PRIMER D

**DESCRIPTION** A fast drying bitumen based primer for all surfaces prior to the application of Densotherm Tape, Densopol 60 and 80 Tapes and Densoclad 40, 50 and 70 Tapes including tropical grades.

**COMPOSITION** Oxidised bitumen in aromatic hydrocarbon solvent.

TYPICAL PROPERTIES	DATA
Specific Gravity	0.940
Covering Capacity	9-11m <sup>2</sup> /litre
Wet Film Thickness	90-110 micron
Dry Film Thickness	45-60 micron
Drying Time	10-15 minutes
Flash Point	23°C minimum
Application Temperature Range	0°C to 55°C

<b>SURFACE PREPARATION</b>	Surfaces must be clean and dry and free from rust, scale and non-adherent coatings. Preferably grit blasted or well wire brushed.
----------------------------	---

Important

Winn & Coales (Denso) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request.

Winn & Coales (Denso) Ltd operate a Quality Management System registered to BS EN ISO 9002 1994 (Certificate No. FM01548).

Winn & Coales (Denso) Ltd, Denso House, Chapel Road, London SE27 0TR, United Kingdom  
Tel: +44 (0) 20 8670 7511 Fax: +44 (0)20 8761 2456 Email: mail@denso.net Website: www.denso.net