



DENSO PENETRATING PRIMER

DESCRIPTION A bitumen based primer for all iron or steel surfaces prior to the application of Denso Ultraseal Tape as part of the Steelcoat 400 System. It allows repositioning of the tape during application whilst developing a strong permanent bond to wire brushed surfaces.

COMPOSITION Oxidised bitumen and hydrocarbon waxes in hydrocarbon solvents.

TYPICAL PROPERTIES	DATA
Solids Content	62% w/w
Specific Gravity	0.92
Covering Capacity	9-11m ² /litre
Wet Film Thickness	90-110 micron
Dry Film Thickness	55-75 micron
Drying Time	30 minutes
Flash Point	23°C MIN
Application Temperature Range	0°C to 55°C

SURFACE PREPARATION	Surfaces must be clean and dry and free from loose rust, scale and non-adherent coatings. Surfaces should be grit blasted, water blasted or well wire brushed to St2.
----------------------------	---

Important

Winn & Coales (Denso) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request.

Winn & Coales (Denso) Ltd operate a Quality Management System registered to BS EN ISO 9002 1994 (Certificate No. FM01548).

Winn & Coales (Denso) Ltd, Denso House, Chapel Road, London SE27 0TR, United Kingdom
Tel: +44 (0) 20 8670 7511 Fax: +44 (0)20 8761 2456 Email: mail@denso.net Website: www.denso.net