


ISSUE	DESCRIPTION	NAME	DATE
I	DEVELOPMENT	JS	26/06/08





BAR CODE No.
5 020837 XXXXXX

CONSTRUCTION:
WHITE WOOD-FREE, ELEMENTAL CHLORINE FREE, NON-COATED
WRITING PAPER
WEIGHT 73 ± 7 gr/sqm, TENSILE STRENGTH (min) 68 N/15mm
OPACITY 82%, SMOOTHNESS (min) 170 sec (bekk)

THICKNESS:
 0.071 ± 0.005

ADHESIVE:
PERMANENT ACRYLIC EMULSION BASED ADHESIVE
QUICK TACK (min) 13 N/25mm ON GLASS
ADHESION, PEEL 20min (min) 16 N/25mm
HIGH RELEASE FORCE 0.11 ± 0.05 N/25mm AT 100m/min
APPLICATION TEMP (min) $+5^{\circ}\text{C}$
SERVICE TEMP -15°C TO $+90^{\circ}\text{C}$

DRG No.: SK6962	STATUS: SK/PR	DESIGNER: J. Softley	UNITS: MM	DATE: 27-Jun-08	PROJECT No.: 638	DESIGN APP.
HASTINGS TEL: 01424 722280 EAST SUSSEX FAX: 01424 442078 TN38 9YJ EMAIL engineering@marshall-tufflex.com				ASSET No.	638	PRODUCTION APP.
 PART CODE: 001257				MATERIAL	SEE NOTE	THIRD ANGLE PROJ.
				COLOUR	SEE NOTE	
				SURFACE FINISH	SEE NOTE	SCALE 1:1

PRODUCT DESCRIPTION:

MT32 Label - Product AA3355