

**DUROMETER (SHORE D) HARDNESS**

TEST METHOD : ASTM D 2240-00  
IDENTIFICATION : Richlite  
CONDITIONING : Tested "as received" at room temperature (73°F & 43% R.H.)

<u>READING</u>	<u>HARDNESS READING</u> face	<u>HARDNESS READING</u> edge
1	91	89
2	90	90
3	90	89
4	91	88
5	90	90
AVERAGE:	90	89
STANDARD DEVIATION:	0.7	0.9
COEFFICIENT OF VARIATION (%):	0.78	1.01

Note : No acceptance/rejection criteria were submitted for the above results.

As a mutual protection to clients, the public and Delsen Testing Laboratories, Inc., this report is submitted for the exclusive use of the client to whom it is addressed. This report applies only to the sample(s) tested and is not necessarily indicative of the qualities of apparently similar or identical products. Use of this report, whether in whole or in part, or of any seals or insignia connected therewith, in any advertising or publicity matter, without prior written authorization from Delsen Testing Laboratories, Inc. is prohibited.